

API CASING

Spec (in)	Weight (lb/ft)	Outside Diameter (in)	Wall Thickness (in)	Drift Diameter (in)	Plain End Wpe (lb/ft)	Type of pipe finishing						
						J55 / K55	M65	L80 / C95	N80	C90 / T95	P110	Q125
4 1/2	9.5	4.5	0.205	3.965	9.41	PS	PS	-	-	-	-	-
	10.5	4.5	0.224	3.927	10.24	PSB	PSB	-	-	-	-	-
	11.6	4.5	0.250	3.875	11.36	PSLB	PLB	PLB	PLB	PLB	PLB	-
	13.5	4.5	0.290	3.795	13.05	-	PLB	PLB	PLB	PLB	PLB	-
	15.1	4.5	0.370	3.701	15.00	-	-	-	-	-	PLB	PLB
5	11.5	5	0.220	4.435	11.24	PS	PS	-	-	-	-	-
	13.0	5	0.253	4.369	12.84	PSLB	PLB	PLB	PLB	PLB	-	-
	15.0	5	0.296	4.283	14.88	PSLB	PLB	PLB	PLB	PLB	-	-
	18.0	5	0.362	4.151	17.95	-	PLB	PLB	PLB	PLB	PLB	PLB
	21.4	5	0.437	4.001	21.32	-	PLB	PLB	PLB	PLB	PLB	PLB
	23.2	5	0.478	3.919	23.11	-	-	PLB	PLB	PLB	PLB	PLB
24.1	5	0.500	3.875	24.05	-	-	PLB	PLB	PLB	PLB	PLB	
5 1/2	14.0	5.5	0.224	4.887	13.71	PS	PS	PS	-	-	-	-
	15.5	5.5	0.275	4.825	15.36	PSLB	PSLB	-	-	-	-	-
	17.0	5.5	0.304	4.767	16.89	PSLB	PLB	PLB	PLB	PLB	PLB	PLB
	20.0	5.5	0.361	4.653	19.83	-	PLB	PLB	PLB	PLB	PLB	-
	23.0	5.5	0.415	4.545	22.56	-	PLB	PLB	PLB	PLB	PLB	PLB
	26.8	5.5	0.500	4.375	26.72	-	-	-	-	P	-	-
29.7	5.5	0.562	4.251	29.67	-	-	-	-	P	-	-	
6 5/8	20.0	6.625	0.228	5.924	19.51	PSLB	PSLB	-	-	-	-	-
	24.0	6.625	0.352	5.796	23.60	PSLB	PSLB	PLB	PLB	PLB	PLB	-
	28.0	6.625	0.417	5.666	27.67	-	PLB	PLB	PLB	PLB	PLB	-
	32.0	6.625	0.475	5.550	31.23	-	-	-	PLB	PLB	PLB	PLB
7	17.0	7	0.231	6.413	16.72	PS	-	-	-	-	-	-
	20.0	7	0.272	6.331	19.56	PS	PS	-	-	-	-	-
	23.0	7	0.371	6.250*	22.65	PSLB	PLB	PLB	PLB	PLB	-	-
	23.0	7	0.371	6.241	22.65	PSLB	PLB	PLB	PLB	PLB	-	-
	26.0	7	0.362	6.151	25.69	PSLB	PLB	PLB	PLB	PLB	PLB	-
	29.0	7	0.408	6.059	28.75	-	PLB	PLB	PLB	PLB	PLB	-
	32.0	7	0.453	6.000*	31.70	-	PLB	PLB	PLB	PLB	PLB	-
	32.0	7	0.453	5.969	31.70	-	PLB	PLB	PLB	PLB	PLB	-
	35.0	7	0.498	5.879	34.61	-	-	PLB	PLB	PLB	PLB	PLB
38.0	7	0.540	5.795	37.29	-	-	PLB	PLB	PLB	PLB	PLB	
7 5/8	24.0	7.625	0.300	6.900	23.49	-	-	-	-	-	-	-
	26.2	7.625	0.328	6.844	25.59	PSLB	PSLB	PLB	PLB	PLB	-	-
	29.7	7.625	0.375	6.750	29.06	-	PSB	PLB	PLB	PLB	PLB	-
	33.7	7.625	0.430	6.640	33.07	-	-	PLB	PLB	PLB	PLB	-
	39.0	7.625	0.500	6.500	38.08	-	-	PLB	PLB	PLB	PLB	PLB
	42.8	7.625	0.562	6.376	42.43	-	-	PLB	PLB	PLB	PLB	PLB
45.3	7.625	0.595	6.310	44.71	-	-	PLB	PLB	PLB	PLB	PLB	
8 5/8	24.0	8.625	0.264	7.972	23.60	PS	PS	-	-	-	-	-
	28.0	8.625	0.304	7.892	27.04	PS	PS	-	-	-	-	-
	32.0	8.625	0.352	7.875*	31.13	PSLB	PSLB	-	-	-	-	-
	32.0	8.625	0.352	7.796	31.13	PSLB	PSLB	-	-	-	-	-
	36.0	8.625	0.400	7.700	35.17	PSLB	PSLB	PLB	PLB	PLB	-	-
	40.0	8.625	0.450	7.625*	39.33	-	PLB	PLB	PLB	PLB	PLB	-
	40.0	8.625	0.450	7.600	39.33	-	PLB	PLB	PLB	PLB	PLB	-
	44.0	8.625	0.500	7.500	43.43	-	-	PLB	PLB	PLB	PLB	-
49.0	8.625	0.557	7.286	48.04	-	-	PLB	PLB	PLB	PLB	PLB	
9 5/8	32.3	9.625	0.312	8.845	31.06	-	-	-	-	-	-	-
	36.0	9.625	0.352	8.765	34.89	PSLB	PSLB	-	-	-	-	-
	40.0	9.625	0.395	8.750*	38.97	PSLB	PSLB	PLB	PLB	PLB	-	-
	40.0	9.625	0.395	8.679	38.97	PSLB	PSLB	PLB	PLB	PLB	-	-
	43.5	9.625	0.435	8.599	42.73	-	PLB	PLB	PLB	PLB	PLB	-
	47.0	9.625	0.472	8.525	46.18	-	-	PLB	PLB	PLB	PLB	PLB
	53.5	9.625	0.545	8.500*	52.90	-	-	PLB	PLB	PLB	PLB	PLB
	53.5	9.625	0.545	8.379	52.90	-	-	PLB	PLB	PLB	PLB	PLB
	58.4	9.625	0.595	8.375*	57.44	-	-	PLB	PLB	PLB	PLB	-
	58.4	9.625	0.595	8.279	57.44	-	-	PLB	PLB	PLB	PLB	-
	32.75	10.75	0.279	10.036	31.23	-	-	-	-	-	-	-
	40.5	10.75	0.350	9.894	38.91	PSB	PSB	-	-	-	-	-
	45.5	10.75	0.400	9.875*	44.26	PSB	PSB	-	-	-	-	-
	45.5	10.75	0.400	9.794	44.26	PSB	PSB	-	-	-	-	-
	51.0	10.75	0.450	9.694	49.55	PSB	PSB	PSB	PSB	PSB	PSB	PSB
55.5	10.75	0.495	9.625*	54.26	-	PSB	PSB	PSB	PSB	PSB	PSB	

API CASING

10 3/4	55.5	10.75	0.495	9.604	54.26	-	PSB	PSB	PSB	PSB	PSB	PSB
	60.7	10.75	0.545	9.504	59.45	-	-	-	-	PSB	PSB	PSB
	65.7	10.75	0.595	9.404	64.59	-	-	-	-	PSB	PSB	PSB
11 3/4	42.0	11.75	0.333	11.000*	40.64	-	-	-	-	-	-	-
	42.0	11.75	0.333	10.928	40.64	-	-	-	-	-	-	-
	47.0	11.75	0.375	10.844	45.60	PSB	PSB	-	-	-	-	-
	54.0	11.75	0.435	10.724	52.62	PSB	PSB	-	-	-	-	-
	60.0	11.75	0.489	10.625*	58.87	PSB	PSB	-	-	-	-	-
	60.0	11.75	0.489	10.616	58.87	PSB	PSB	-	-	-	-	-
	65.0	11.75	0.534	10.625*	64.03	-	-	-	-	-	-	-
	65.0	11.75	0.534	10.526	64.03	-	-	-	-	-	-	-
13 3/8	48.0	13.375	0.333	12.559	46.02	-	-	-	-	-	-	-
	54.5	13.375	0.380	12.459	52.79	PSB	PSB	-	-	-	-	-
	61.0	13.375	0.430	12.359	59.50	PSB	PSB	-	-	-	-	-
	68.0	13.375	0.480	12.259	66.17	PSB	PSB	-	-	-	-	-
	72.0	13.375	0.514	12.250*	70.67	-	-	-	-	-	-	-
	72.0	13.375	0.514	12.191	70.67	-	-	-	-	-	-	-
16	65.0	16.0	0.375	15.062	62.64	-	-	-	-	-	-	-
	75.0	16.0	0.438	14.936	72.86	PSB	PSB	-	-	-	-	-
	84.0	16.0	0.495	14.822	82.05	PSB	PSB	-	-	-	-	-
	109.0	16.0	0.656	14.500	107.60	P	-	P	P	-	P	P
18 5/8	87.5	18.625	0.435	17.567	84.59	PSB	PSB	-	-	-	-	-
20	94.0	20	0.438	18.936	91.59	PSLB	PSLB	-	-	-	-	-
	106.5	20	0.500	18.812	104.23	PSLB	PSLB	-	-	-	-	-
	133.0	20	0.635	18.542	131.45	PSLB	-	-	-	-	-	-

P: Plain End; S: Short Round Thread; L: Long Round Thread; B: Buttress Thread.

*: Drift Diameter for most common bit size.